




















Product quality		
Format	1207 x 216 x 9,6 mm	
Packaging	Pack: 7 elements / 1,825 m ² / 17,91 kg	
	Pallet: 36 packs / 65,70 m ² / 659,76 kg	
Tolerances EN ISO 20326:2018		
Squareness of the elements (≤ 0.20 mm)	≤ 0,20 mm/m	
Determination of linearity (≤ 0.30 mm/m)	≤ 0,15 mm/m	
Flatness concave / convex	lengthwise (≤ 0.50/≤ 1.0 %)	≤ 0,35/≤ 1,0 %
	wide (≤ 0.10/≤ 0.15 %)	≤ 0,10/≤ 0,10 %
Surface flushness	(average ≤ 0.10 mm)	average ≤ 0.10 mm
	(max. ≤ 0.15 mm)	max. ≤ 0.15 mm
Opening between installed elements	(average ≤ 0.15 mm)	average ≤ 0.05 mm
	(max. ≤ 0.20 mm)	max. ≤ 0.10 mm
Dimensional change due to changing air humidity % (≤ 0,25)	≤ 0,1%	

Guarantee (According Parador guarantee conditions)		Notes
Domestic area	Commercial area	- not suitable for all-over adhesion - cleaning and maintenance see instructions - technical changes reserved
Lifetime	10 years	
   		

Classification			
		Test method	Rating
	Utility class 23 domestic areas with intensive use	EN ISO 20326	Living room, hall, kitchen, home office
	Utility class 33 commercial areas with intensive use	EN ISO 20326	Classrooms, open-plan offices, shops
	Wear layer	ISO 24340	0,55 mm
	Surface Coating		PUR
	Reaction to fire	EN 13501-1	B _f s1
	Slip resistance	EN 13893 EN 14041	μ ≥ 0,35 DS
	Staining resistance	EN 423	Grade 0, no visible changes
	Light fastness	EN ISO 105 – B02	Blue wool scale: Stage ≥ 6
	Resistance to roller castor chairs	ISO 4918	Type W, no visible changes
	Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN ISO 10456	0,068 m ² *K/W
	Moving a furniture leg	EN 424	No visible changes
	Indentation-residual	EN 433	≤ 0,10 mm
	Formaldehyde emission (E1 = 0.1 ppm)		≤ 0,05 ppm
	Acoustical - Impact noise reduction	ISO 717-2	15 dB (on Akustik-Protect 100) 16 dB (on PE film)
	Thickness swelling	ISO 24336 (≤ 15%)	≤ 15%
	Locking strength	ISO 24334	Long side ≥ 1,0 kN/M Short side ≥ 2,0 kN/M
	Antimicrobial activity	ISO 22196	Antibacterial
	Slip resistance on an inclined plane	DIN 51130	Antique, brushed, rustic texture: R 9 / Wood texture : R 10
	Disposal	EAK-Code-number	17 02 03

Changed:	QMB Parador	File:	20190901_PA_TDS_Vinyl_Classic-2030_EN
Date:	01.06.2012	Latest update at:	www.parador.eu/service/catalogues-downloads/technical-data-sheets
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.09.2019